

Comparison of the principal kinds of fine quality Faience, as shown at the Exhibition in Paris, in 1867, as regards their quality and price.

DESCRIPTION OF FAIENCE.	Hardness	Grain.	Price.	Price.
1. SUPERIOR QUALITY.				
			Francs.	Francs.
Sarreguemines China, France,	0k.625	8.25	2.0	3.10
Minton & Company's white glaze,	0k.530	12.35	2.95	3.25
Rörstrand, Sweden,	0k.440	9.43	-	3.00
Gustafberg, Sweden,	0k.480	11.24	2.20	-
2. SECOND QUALITY.				
Choisy-le-Roi, "Granite China" (France),	0k.420	11.23	1.95	3.15
Stoneware of Villerry and Boch (Prussia),	0k.415	13.14	2.20	3.80
Stone-China of Pinder Bourne (England),	0k.485	10.00	2.75	2.95
3. ORDINARY WARE.				
Opaque of Sarreguimines, France,	0k.620	13.25	1.50	-
Opaque porcelain of Gien, France,	0k.375	14.50	1.55	2.60
Cream colored ware, Minton & Co., Eng.,	0k.400	8.20	1.58	-
Opaque porcelain of Creil, France,	0k.505	10.14	1.55	-
Opaque porcelain of Montereau, France,	0k.450	15.40	1.55	2.50
Half-porcelain of Choisy-le-Roi, France,	0k.390	11.31	1.55	2.25
Cream colored ware, Copeland & Co., Eng.,	0k.340	8.64	2.60	3.15
Cream colored ware, Wedgwood, Eng., .	0k.320	8.57	2.10	2.95